



versalis

Technical Data Sheet

www.versalis.eni.com

info.polyethylene@versalis.eni.com

FLEXIRENE[®]

MS 40 A

LLDPE

Linear low density polyethylene

Flexirene MS 40 A is a linear low density polyethylene (LLDPE) with antioxidants, suitable for injection moulding application.

Parts made by Flexirene MS 40 A are characterised by a good balance between impact resistance and rigidity.

Main Application

Flexirene MS 40 A is recommended for the production of large sized articles, houseware and toys. Flexirene MS 40 A is characterized by a high flowability which make it ideal for masterbatches preparation for LDPE and LLDPE.

Main Properties

Resin Properties

	Value	Test Method	Unit
Melt Flow Rate (190 °C/2.16 kg)	27	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Density	0.930	g/cm ³	ISO 1183
Melting Point	121	°C	Internal method
Brittleness temperature	< - 70	°C	ASTM D 746
Vicat softening point (1 kg)	103	°C	ISO 306/A

Mechanical Properties *

	Value	Unit	Test Method
Tensile stress at yield	11	MPa	ISO 527
Tensile strenght at break	12	MPa	ISO 527
Elongation at break	> 500	%	ISO 527
Flexural modulus	300	MPa	ISO 178
Hardness Shore D	52	-	ISO 868 A
FallingWeight:	-	J/mm	ISO 6603/2
Izod impact strength, notched	-	J/m	ISO 180/A
Environmental Stress Cracking Resistance (ESCR)	-	h	ISO 22088

* Values are referred to injection moulded specimens. Actual properties are typical and may vary depending upon operating conditions.

Processing notes

Flexirene MS 40 A is easy to mould with the newest injection moulding machines. Results are excellent.

Typical processing conditions (*)

Temperature profile of the barrel (°C) 160 - 210

Temperature of the mould (°C) 10 - 40

Storage and Handling

Flexirene MS 40 A is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight.

Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

Availability

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

Food Contact Status

Flexirene MS 40 A complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL SERVICE

Versalis S.p.A.
Piazza Boldrini, 1
20097 S.Donato Milanese, Italia
Tel. +39 02 520.1
Fax + 39 02 520.42436

Polimeri Europa SAS
1 Route des Dunes BP 59
F-59279 MARDYCK - France
Tel. +33 3 28235515
Fax +33 3 28235520

Versalis S.p.A.
Via Taliercio, 14
46100 Mantova, Italia
Tel. +39 0376 305667
Fax +39 02 52043

HEADQUARTER

Versalis S.p.A.
Piazza Boldrini, 1
20097 S.Donato Milanese, Italia
Tel. +39 02 520.1
Fax + 39 02 520.42436

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

Versalis is available to provide the guaranteed values for each product on demand.